



Technical Fact Sheet

CFF[®] V125-1 Fibrillated Acrylic Pulp

General Description

CFF[®] V125-1 is a fibrillated acrylic pulp with similar surface area to CFF[®] V110-1, but with a reduced average fiber length and smaller fiber diameter. This highly fibrillated structure contributes to mix uniformity, improved particle retention, and dust suppression in dry mix formulations. Due to its shorter fiber length, CFF[®] V125-1 pulp provides a lower increase in mix bulk volume relative to CFF[®] V110-1 or aramid pulp.

Comparison of CFF[®] Fibrillated Fiber Properties

Typical Properties	Units	CFF [®] V110-1	CFF [®] V125-1
Canadian Standard Freeness	ml	250	400
Fiber Length	mm	6.5	5
Fiber (Trunk) Diameter	micron	25	16
BET Surface Area	m ² /g	50	50
Screen Fineness (14 mesh)	%	40	<10
Fluff Volume, Minimum	ml	375	340
Moisture Content	%	2	15
Finish Level	%	0	0
Additive	%	0	0
pH	-	7	7
Chemical Composition	-	AN/VA	AN/VA
Appearance	-	Fine White Pulp	Fine White Pulp

IMPORTANT NOTICE

The information and statements herein are believed to be reliable, but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.

Sterling Fibers, Inc.
5005 Sterling Way
Pace, FL 32571

TEL: (850) 994-5311 x618
FAX: (850) 994-2579
EMAIL: jhagerott@sterlingfibers.com